

# DURMAT DUR 600 AC

<b>Standards</b>	DIN 8555	E 6- UM - 60 GP
------------------	----------	-----------------

**Approvals** ---

**Characteristics** DURMAT DUR 600 AC is an AC-weldable universal hard surfacing electrode with 120 % recovery for rebuilding of machine parts subject to combined wear from abrasion and impact. Suitable for deposits on mild steel, steel castings and manganese steel.  
The pure weld deposit is only machinable by grinding.  
The electrode has a soft but intensive welding character, a fine-structured seam surface and excellent slag-removal properties.  
On high-carbon and crack-sensitive base materials, should be preheated to 200°– 300°C, depending on their composition and thickness. On highly crack-sensitive base materials and manganese steel, a buffer layer of DURMAT DUR 4370 MPR or DURMAT DUR MnCr is recommended.

**Typical applications** Rollers, dredger chains, conveyors, hammers, dredger equipment, mining and earth-moving equipment

**Operating temperature**

**Welding instructions** Guide electrode almost vertically with a short arc.

<b>Hardness and recommendations for heat treatment</b>	<b>HRc as welded</b>	<b>Annealing: 5 h</b>	<b>Hardening oil - air</b>
	ca. 59	780°C – 820°C	1000°C – 1050°C

<b>Weld metal analysis (typical. wt %)</b>	<b>C</b>	<b>Si</b>	<b>Mn</b>	<b>Cr</b>
	0,6	1,7	0,4	9

**Current** = + / ~ 50 V

**Welding positions** PA. PB. PC. PD. PE

**Rebaking** 1 h. 350 °C + (if required)

Dia./Length	Amperage (A)	Pcs./ packet	Pcs./ carton	kg / 1000	kg / packet	kg / carton
2,5 x 350	60 – 90	221	884	22.6	5,0	20,0
3,2 x 350	90 – 120	135	540	37.0	5,0	20,0
4,0 x 450	110 – 160	86	344	76.0	6,0	24,0
5,0 x 450	150 – 200	56	225	106,8	6,0	24,0
6,0 x 450	180 – 250	37	148	162,6	6,0	24,0