



Industrial Comercial Chile Ltda.

... En la búsqueda de Soluciones Tecnológicas.

Proveedores de Industria y Minería

E-Mail: comchile@comercialchile.cl

Web Site: www.comercialchile.cl



FICHA TECNICA

MATERIAL : Granalla Angular

Chemical Composition

Chemical composition:	C:0.8-1.20; Si:0.60-1.20; Mn:0.70-1.20; S:≤0.03; P:≤0.03
Density:	>7.3g/cm ³
Hardness(± 3HRC):	HRC 52-58

Specification:

Number of screen	Standard (mm)	Screw mesh (inch)	G10	G12	G14	G16	G18	G25	G40	G50	G80	G120
			SG240	SG200	SG170	SG140	SG120	SG100	SG70	SG50	SG30	SG20
7	2.8	0.111	0									
8	2.36	0.0937	-	0								
10	2.00	0.0789	80	-	0							
12	1.70	0.0661	90	80	-	0						
14	1.40	0.0555		90	80	-	0					
16	1.18	0.0469			90	85	-	0				
18	1.00	0.0394				85	75	-	0			
20	0.85	0.0331					-	-	-			
25	0.71	0.0278					85	70	-	0		
30	0.60	0.0234						-	-	-		
35	0.50	0.0197						-	-	-		
40	0.425	0.0165						80	70	-	0	
45	0.355	0.0139							-	-	-	
50	0.300	0.0117							80	65	-	0
80	0.180	0.007								75	65	-
120	0.125	0.0049									75	60
200	0.075	0.0029										70

SS-JIS S-SAE O-ALL pass The Figure in the square indicates the percentage allowed to remain on the screen.

Para mayor información:

Industrial Comercial Chile Ltda.

Cerro Los Cóndores N° 9901 Quilicura / Santiago / Chile

☎: (56-2) 25204900

✉: comchile@comercialchile.cl

🌐: www.comercialchile.cl

